

## Technical Data Sheet

**MATERIAL PROPERTIES\*:**      MICA-GR<sup>®</sup>

**DESCRIPTION:**                      Mica GR<sup>®</sup> is a material consisting of two outer layers of Mica on a pegged steel insert.

The Mica is an alumina silicate of mineral origin, and has a laminar and non-fibrous structure. This material gives Mica-GR<sup>®</sup> its thermal characteristics and chemical resistance to solvents, mineral oils and other substances.



**COLOUR:**                              Gold/Green

**SERVICE:**                              Generally for sealing in high temperature applications, as in automotive exhaust manifolds and joints, gas turbines, gas and oil burners, and heat exchangers. In some types of applications a protective eyelet is recommended for the media bore.

**SPECIFICATIONS (1.3MM):**

Compressibility ASTM F36J:	%	24
Recovery ASTM F36J:	%	>40
Density Prior to Lamination:	g/cm <sup>3</sup>	1.9
Maximum Application temperature:	°C	1000

**Fuel & Oil Resistance:**

ASTM Fuel B-5 Hours @ 23°C		
Weight Increase:	%	7 - 14
Thickness Increase:	%	0
ASTM Oil #3 - 5 Hours @ 150°C		
Weight Increase:	%	13 - 18
Thickness Increase:	%	1 - 8%

**AVAILABILITY:**

Sheeting:	1200mm x 1000mm
Thickness:	1.3mm, 2.0mm, 3.0mm

Notes: \* This is a general guide and should not be the sole means of selecting or rejecting this material. This data sheet covers basic information, for more comprehensive information, please contact us.

**Asbestos Free**



Certificate Number: 14352  
 ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

**Web: [www.epdm.co.uk](http://www.epdm.co.uk)**  
**E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)**

**Contact**

Telephone: +44 (0)1625 573971  
 FAX: +44 (0)1625 573250  
 Munsch & Co/PTM Ltd  
 Units AG2/3 Clarence Mill  
 Clarence Road, Bollington  
 Macclesfield, Cheshire  
 SK10 5JZ  
 United Kingdom