

# Technical Data Sheet

## Nitrile Rubber BS2751 BA60

### CHEMICAL DESCRIPTION:

Acrylonitrile Butadiene, Nitrile Butadiene Rubber (NBR)

### PHYSICAL PROPERTIES

TENSILE STRENGTH:	10 MPa (Min)
ELONGATION AT BREAK:	350%
HARDNESS RANGE:	60° Sh. A +/- 5°
HEAT RESISTANCE:	-30° - + 110°C
SPECIFIC GRAVITY:	1.28 +/-0.02
COMPRESSION SET:	30%
22 Hours @ 70°C	



### CHEMICAL RESISTANCE

WATER:	Good to Excellent	
DILUTE ACIDS & BASES:	Good	
ALKALIS:	Good to Excellent	
OZONE:	Poor	
HYDROCARBONS:	Moderate	
SOLVENTS:	Moderate	
VOLUME SWELLING:	ASTM 5 Inc. Vol Oil %	IRM903 Inc. Vol. Oil %
70 HOURS @ 70°C	5	20

This is a British Standard Nitrile Rubber to BS2751. Using a recognised standard ensures that the material will always comply to it no matter who the manufacturer is.

This ensures continuity of operation which can vary if non-standard materials are used.

**ELASTOMERS**



Certificate Number: 14352  
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

### Contact

Telephone: +44 (0)1625 573971  
FAX: +44(0)1625 573250  
PTM Ltd  
Units AG2/3 Clarence Mill  
Clarence Road, Bollington  
Macclesfield, Cheshire  
SK10 5JZ  
United Kingdom