

# Technical Data Sheet

## Nitrile Rubber WCMP559

### CHEMICAL DESCRIPTION:

Acrylonitrile Butadiene, Nitrile Butadiene Rubber (NBR)

### PHYSICAL PROPERTIES

TENSILE STRENGTH:	10 MPa
ELONGATION AT BREAK:	330%
ABRASION RESISTANCE:	Good
HARDNESS RANGE:	70° Sh. A +/- 5°
HEAT RESISTANCE:	-20° - + 80°C (90°C Short Term)
COMPRESSION SET:	22 Hrs @ 100°C = +40% Change



### CHEMICAL RESISTANCE

WATER:	Good to Excellent
DILUTE ACIDS & BASES:	Good
ALKALIS:	Good to Excellent
OZONE:	Poor
HYDROCARBONS:	Moderate
SOLVENTS:	Moderate

	Inc. in Hardness Sh. A	Inc. in Tensile %	Inc. in Elongation %
THERMAL AGEING: 70 HOURS @ 100°C	+10	-10	-35
VOLUME SWELLING: 70 HOURS @ 30°C	Fuel B Inc. (ISO 1817) %	20	IRM903 Inc. Vol. Oil %
70 HOURS @ 70°C			10

This is a high grade Nitrile rubber with good mechanical properties. It has good oil resistance, recommended for most aliphatic and aromatic oils. It also has good resistance to Benzene and moderate resistance to acids.

**ELASTOMERS**



Certificate Number: 14352  
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

#### Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom