

Technical Data Sheet

Silicone (WCMVMQ)

CHEMICAL DESCRIPTION: Polydimethylsiloxane containing methyl (MQ) or vinyl (VMQ)

PROPERTIES

ASTM classification:	MQ & VMQ
Typical applications:	Food and medical applications
Advantages:	Excellent resistance to high and low temperatures
Disadvantages:	Poor tensile strength Poor resistance to oils and non-polar solvents
Available hardness range (Sh. A):	20 - 85
Upper continuous service temp. (°C):	225
Min. temp. for sealing applications. (°C):	-60
Minimum non-brittle temp. (°C):	-80
Tensile strength (up to):	11 MPa
Elongation at break (up to):	600%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom