


Technical Data Sheet

25% GLASS FIBRE FILLED PTFE (WCM405)

DESCRIPTION: Polytetrafluoroethylene

PHYSICAL PROPERTIES

SPECIFIC GRAVITY:	2.2 - 2.26 g/cm ³
COEFFICIENT OF LINEAR THERMAL EXPANSION 25-100 °C:	7.5 - 11 (10 ⁻⁵ (mm/mm)/°C)
HARDNESS SHORE D	≥ 70
TENSILE STRENGTH:	≥ 17 N/mm ²
ELONGATION AT BREAK:	≥ 230 %
COMPRESSIVE STRENGTH AT 1% DEFORMATION:	8 - 9 N/mm ²
DEFORMATION UNDER LOAD: (24 h 13.7 N/mm ² 23 °C):	≤ 10 %
PERMANENT DEFORMATION: (AS ABOVE, AFTER 24-H RELAXATION)	≤ 6.5 %
KINETIC COEFFICIENT OF FRICTION:	0.13
WEAR FACTOR @ PV100:	10 - 15 $\frac{\text{cm}^3 \cdot \text{min} \cdot 10^{-8}}{\text{Kg} \cdot \text{m} \cdot \text{h}}$



PTFE

The base characteristics of PTFE are the ones offering a unique combination of:

- Low coefficient of friction
- Excellent chemical inertness
- Non-adhesive surface
- Wide temperature range withstanding (-200° C to +260° C)
- Excellent dielectric properties

Flexibility strength, plastic memory and hardness, are additional characteristics of PTFE products.

PTFE is practically inert to all chemical products, except for some alkaline metals, for example, chlorotrifluoruro and for basic fluorine at high temperatures and pressures.

PTFE is considered one of the most stable materials from the thermal point of view.

Up to a service temperature of 260° C PTFE does not change its own physical and molecular properties.

With this grade being 25% Glass Fibre filled it exhibits enhanced wear resistance and enhanced chemical resistance (except for alkali and hydrofluoric acid).

We also offer Carbon, Bronze and Graphite filled PTFE.

Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom



Certificate Number: 14352
ISO 9001

