

Technical Data Sheet

Black Shotblast Rubber WCMN04

CHEMICAL DESCRIPTION:

Styrene-Butadiene Rubber, SBR

PHYSICAL PROPERTIES

TENSILE STRENGTH:	14.0 (MPa)
SPECIFIC GRAVITY:	1.3
ELONGATION AT BREAK:	300% Min
ABRASION RESISTANCE:	Good
HARDNESS RANGE:	60° Sh. A (+ or - 5°)
TEMPERATURE RANGE:	-40° - +85° C
OZONE RESISTANCE:	Fair
ABRASION RESISTANCE:	150mm ³



CHEMICAL RESISTANCE

WATER:	Good to Excellent
ACIDS:	Good
ALKALIS:	Good
OILS:	Poor
FUELS AND PETROLEUM SOLVENTS:	Poor
KETONES:	Fair

Wear Resistant rubber is specifically designed to resist mechanical wear and is therefore used in a multitude of modern industries, everything from mining and quarries to steel works and foundries.

ELASTOMERS



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom