

Technical Data Sheet


E.P.D.M. Rubber WCM-M228

CHEMICAL DESCRIPTION:

Ethylene Propylene Diene Co-Polymer, EPDM

PHYSICAL PROPERTIES

TENSILE STRENGTH:	7 (MPa)
COMPRESSION SET: 22 Hours @ 70° C	35%
SPECIFIC GRAVITY:	1.38
ICI M228 COMPLIANT:	Yes
ELONGATION AT BREAK:	250% Min
ABRASION RESISTANCE:	Poor
HARDNESS RANGE:	80° Sh. A (+ or - 5°)
TEMPERATURE RANGE:	-15° - +120° C
OZONE RESISTANCE:	Excellent



CHEMICAL RESISTANCE

WATER:	Excellent
ACIDS:	Very Good
ALKALIS:	Excellent
OILS:	Poor
FUELS AND PETROLEUM SOLVENTS:	Poor
KETONES:	Good

EPDM's are resistant to many chemicals and solvents particularly water, phosphate ethers, ketones, alcohols together with various acids and alkalis.

EPDM's have good resistance to many corrosive chemicals, most inorganic chemical products, mineral acids, detergents and glycol.

This material meets ICI M228 specification for use with acids.

ELASTOMERS



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom