

Technical Data Sheet

Flexitallic 1065

Flexitallic 1065 compression packing, is a high quality packing constructed by X-braiding PTFE (100% GFO®) yarn impregnated with graphite and a high temperature lubricant.

Flexitallic 1065 can be used in rotary, reciprocating and static sealing applications handling most chemical media. Exceptions are molten alkali metals and strong oxidizing media such as oleum, aqua regia and fuming nitric acid. It is particularly good in sealing water, steam, slurries, oils, acids and alkalis. Typical sealing applications include petrochemical, chemical, brewing, paper and pulp industries.



- Materials of construction: PTFE (100% GFO®) yarn impregnated with graphite and high temperature lubricant.
- Colour: Black.
- Typical applications: Pumps, Mixers and Control Valves.
- Approvals: FDA compliance



GFO® is a trademark of W.L. Gore & Associates Inc.

Temperature: Maximum	260 °C (500 °F)
Minimum	-85 °C (-120 °F)
Pressure: Maximum	Rotating – 2 MPa (290 psi) Valve – 20 MPa (2900 psi) Reciprocating – 15 MPa (2174 psi)
Speed: Maximum	Rotating – 20 m/s (3937 fpm) Valve – 2 m/s (394 fpm) Reciprocating – 2 m/s (394 fpm)
pH Range	0 – 14
Standard Sizes (mm sq.)	3.2, 5.0 - 20m spools. 6.0, 6.5, 8.0, 9.5, 10.0, 11.0, 12.0, 12.5, 14.0, 14.5, 16.0, 18.0, 19.0, 22.0, 25.0 – 8m spools

Compression Packing



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

Web: www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom