

Technical Data Sheet

Epichlorohydrin Rubber (WCMECO)

CHEMICAL DESCRIPTION: Polymers based on polyepichlorohydrin which may also contain ethylene oxide and allyl glycidyl ether.

PROPERTIES

ASTM classification: CO, ECO

Typical applications: Seals, gaskets, diaphragms, cable jackets and belting

Advantages: Excellent ozone resistance
Good resistance to oils
Fire resistance

Disadvantages: Poor resistance to some non-polar solvents
Poor steam resistance

Available hardness range (Sh. A): 40 - 90

Upper continuous service temp. (°C): 125

Min. temp. for sealing applications. (°C): -35

Minimum non-brittle temp. (°C): -45

Tensile strength (up to): 20 MPa

Elongation at break (up to): 400%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44(0)1625 573250

PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom