

## Technical Data Sheet

### Natural Rubber (BS1154 Z60)

**CHEMICAL DESCRIPTION:** Polyisoprene

**PHYSICAL PROPERTIES**

TENSILE STRENGTH: 17.0 (MPa) Min.

SPECIFIC GRAVITY: 1.12

ELONGATION AT BREAK: 400% Min

COMPRESSION SET:  
22 Hours @ 70° C 30% Max.

ABRASION RESISTANCE: Good

HARDNESS RANGE: 60° Sh. A (+ or - 5°)

TEMPERATURE RANGE: -40° - +80° C

OZONE RESISTANCE: Poor

RESILIENCE: Excellent

**CHEMICAL RESISTANCE**

WATER: Good to Excellent

ACIDS: Good

ALKALIS: Good

OILS: Poor

FUELS AND PETROLEUM SOLVENTS: Poor

KETONES: Fair

Recommended for low to medium cost products where good resilience and toughness are prime considerations. Not recommended where resistance to heat or oils is required.

This is a British Standard Natural Rubber to BS1154. Using a recognised standard ensures that the material will always comply to it no matter who the manufacturer is. This ensures continuity of operation which can vary if non-standard materials are used.



**ELASTOMERS**



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

Contact

Telephone: +44 (0)1625 573971  
Polymer Trade Manufacturing Ltd  
Units AG2/3 Clarence Mill  
Clarence Road, Bollington  
Macclesfield, Cheshire  
SK10 5JZ  
United Kingdom