



Technical Data Sheet

Chlorobutyl Rubber (WCMCIIR)

CHEMICAL DESCRIPTION: Derivative of butyl rubber which has been reacted with chlorine in a continuous process.

PROPERTIES

ASTM classification:	CIIR
Typical applications:	Inner tyre tubes, breathing apparatus for defence and fire services
Advantages:	Low gas permeability Excellent ozone resistance Good steam resistance Good fire resistance
Disadvantages:	Poor resistance to oils and non-polar solvents
Available hardness range (Sh. A):	35 - 90
Upper continuous service temp. (°C):	130
Min. temp. for sealing applications. (°C):	-50
Minimum non-brittle temp. (°C):	-70
Tensile strength (up to):	18 MPa
Elongation at break (up to):	650%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
FAX: +44 (0)1625 573250
Munsch & Co/PTM Ltd
Units AG2/3 Clarence Mill
Clarence Road, Bollington
Macclesfield, Cheshire
SK10 5JZ
United Kingdom