



Technical Data Sheet

Tetrafluoroethylene-perfluorovinylether-ethylene terpolymer (WCMFEPM T)

CHEMICAL DESCRIPTION:

Fluorocarbon terpolymer of tetrafluoroethylene, perfluorovinylether and ethylene, which has been designed for use in extreme environments.

PROPERTIES

ASTM classification:

FEPM

Typical applications:

Seals, O-rings, gaskets and packers for oil exploration and production

Advantages:

Excellent high temperature resistance
Outstanding chemical resistance (including acids & bases)
Excellent resistance to oils and non-polar solvents
Excellent ozone and weathering resistance
Excellent steam resistance

Disadvantages:

Poor low temperature performance

Available hardness range (Sh. A):

70 - 95

Upper continuous service temp. (°C):

250

Min. temp. for sealing applications. (°C):

-9

Minimum non-brittle temp. (°C)

-10

Tensile strength (up to):

23 MPa

Elongation at break (up to):

300%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971

FAX: +44 (0)1625 573250

Munsch & Co/PTM Ltd

Units AG2/3 Clarence Mill

Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom