

Technical Data Sheet

Peroxide-cured fluoroelastomer terpolymer(WCMFKM 2P)

CHEMICAL DESCRIPTION:

Type 2 FKM are fluorocarbon terpolymers based on vinylidene fluoride, tetrafluoroethylene fluoride and hexapropylene fluoride. They may be cured using bisphenol (FKM2) or peroxide (FKM2P).

PROPERTIES

ASTM classification:

FKM Type 2

Typical applications:

Seals and gaskets for chemical processing, power and utilities

Advantages :

Excellent high temperature resistance
Good resistance to oils and most non-polar solvents
Excellent ozone and weathering resistance

Disadvantages:

Limited steam resistance
Poor low temperature performance

Available hardness range (Sh. A):

50 - 95

Upper continuous service temp. (°C):

240

Min. temp. for sealing applications. (°C):

-10

Minimum non-brittle temp. (°C):

-35

Tensile strength (up to):

20 MPa

Elongation at break (up to):

250%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
FAX: +44 (0)1625 573250
Munsch & Co/PTM Ltd
Units AG2/3 Clarence Mill
Clarence Road, Bollington
Macclesfield, Cheshire
SK10 5JZ
United Kingdom