

## Technical Data Sheet

### Scapa 3257

PVC Single Sided Foam Tape

medium hard, grey, waterseal

#### DESCRIPTION

Scapa 3257 is primarily a foam compression sealant. The product is grey. The foam is predominantly closed celled and is a medium hardness foam. An acrylic pressure sensitive adhesive is coated on one side, and the product has a paper release liner on the other non-adhesive face. Scapa 3257 will act as a water seal and air/dust seal when compressed.

#### APPLICATIONS

- For preventing electrolytic corrosion.
- For cushioning.
- For gap filling.
- For anti-slip mounting.

#### PRODUCT BENEFITS

- Minimum 30% compression required to effect a water seal.
- Service temperature: -30°C to +70°C.
- Application temperature: +10°C to +40°C.
- Shelf life of 1 year from dispatch.
- Good resistance to dilute acids and alkalis.
- Paper release liner on the non-adhesive face, reducing dimensional change during application.
- Very good ultraviolet {UV} light resistance.
- Resistance to abrasion, corrosion and moisture.
- Suitable for indoor and outdoor environments.
- Medium hardness multipurpose foam seal, with similar properties to Neoprene.
- No known hazards associated with this product.
- Predetermined dimensional sealant reduces waste.
- Clean to use / clean edge finish.

SPONGE & FOAM



Certificate Number: 14352  
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

#### Contact

Telephone: +44 (0)1625 573971

FAX: +44 (0)1625 573250

Munsch & Co/PTM Ltd

Units AG2/3 Clarence Mill  
Clarence Road, Bollington

Macclesfield, Cheshire

SK10 5JZ

United Kingdom

**SPONGE & FOAM**

**Accreditation:**

Fire rated to DIN 4102 part 1, B2.

Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free).

Accredited to UL®50E File No. MH48938

**TECHNICAL PROPERTIES**

Technical Property	Nominal Value	Unit	Test Method
10 Minute 180° Peel Adhesion	5	N/25mm	Scapa F9
Compression Deflection After 1 Minute	2.7	Ncm <sup>-2</sup>	Scapa F4
Elongation at Break	>155	%	Scapa F17
Foam Density	130	Kg/m <sup>3</sup>	Scapa F2
Force To Compress By 30 %	3.2	Ncm <sup>-2</sup>	Scapa F4
Shore Hardness {00} Scale	35	"00"	Scapa F16
Tensile Strength	30	Ncm <sup>-2</sup>	Scapa F17
Thermal Conductivity (k)	0.052	Wm <sup>-1</sup> K <sup>-1</sup>	Lee's Disc

**STANDARD PRESENTATIONS**

- Core: 76mm plastic
- Formats: Logs; Rolls; Die Cuts; Spools
- Thickness : 1.5; 3.0; 4.5; 6.0 mm

**RECOMMENDATIONS**

Surfaces must be clean, dry, free from grease and dirt. Recommended cleaning agent is Propan-2-ol, {IPA}. Please note manufacturer's safety instructions should be followed and customers are recommended to ensure compatibility of the solvent with their substrate. Ideal bonding substrates are those which are: clean, dry, flat, smooth, dust free & non-porous. Low temperatures may increase the risk of condensation, reducing the tack of the product. Life expectancy will vary with temperature and humidity. Product may be applied by hand direct from a roll applying even pressure. Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.



Certificate Number: 14352  
 ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

**Contact**

Telephone: +44 (0)1625 573971  
 FAX: +44 (0)1625 573250  
 Munsch & Co/PTM Ltd  
 Units AG2/3 Clarence Mill  
 Clarence Road, Bollington  
 Macclesfield, Cheshire  
 SK10 5JZ  
 United Kingdom