

Technical Data Sheet

White CR/EPDM Blend Sponge (WCM402)

POLYMER: EPDM/CR (Neoprene)

PHYSICAL PROPERTIES

CELL STRUCTURE: Closed Cell
DENSITY: 116 Kg/m³ (Avg.)
TEMPERATURE RANGE: -40° - +70° C
 (Intermittent Temp. 90° C)
TENSILE STRENGTH: 300 KN/m² (Approx.)
COMPRESSION @ 25% DEFLECTION: 42 KPa
COMPRESSION @ 50% DEFLECTION: 112 KPa
COMPRESSION SET: 21.1%
 50%, 22 Hrs @ 40°
ELONGATION AT BREAK: 150%



RESISTANCE

AIR & UV: Excellent
FIRE/FLAMMABILITY: Pass (FMVSS302)
OIL: Poor
ACIDS: Good
ENVIRONMENTAL PROTECTION: CFC & HFC Free—Recyclable

This material is a blend predominantly of EPDM with a small amount of Chloroprene. Being a closed cell sponge means the cells are not interlinked.

Blended sponge can be a more economical, as well as being a highly versatile product taking strengths from both materials it is manufactured from. Blended rubbers also offer an advantage over standard EPDM - with greater Fire retardancy levels.

It is a flexible product, which can also dampen vibration, has good acoustic and sound deadening properties and has shock / energy absorbent qualities.

Materials available from block, sheet or split into a continuous roll as well as strip, gasket and cut parts to specified shapes and sizes, either plain or with a range of self-adhesive backings.

SPONGE & FOAM



Certificate Number: 14352
 ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
 FAX: +44 (0)1625 573250
 Munsch & Co/PTM Ltd
 Units AG2/3 Clarence Mill
 Clarence Road, Bollington
 Macclesfield, Cheshire
 SK10 5JZ
 United Kingdom